

(12) **UK Patent Application** (19) **GB** (11) **2 340 835** (13) **A**

(43) Date of A Publication 01.03.2000

(21) Application No 9818604.2

(22) Date of Filing 26.08.1998

(71) Applicant(s)
Pvax Ploymers Ltd
(Incorporated in Ireland)
Castle River House, 14/15 Parliament Street,
Dublin 2, Ireland

(72) Inventor(s)
Henry Guy Stevens

(74) Agent and/or Address for Service
Mathys & Squire
100 Grays Inn Road, LONDON, WC1X 8AL,
United Kingdom

(51) INT CL⁷

**C08L 29/04 , B29C 47/00 69/00 , C08K 5/00 13/02
13/06 // (C08K 5/00 5:053 5:20) (C08K 13/02 3:26
5:04 5:20)**

(52) UK CL (Edition R)

**C3K KLA KMA K124 K201 K241 K243 K244 K270
B5A AA1 AC A1R102 A1R314C1F A1R420 A1R428
A1R449 A20T17 A20T23 A20T24
C3V VCX
C3W W301
U1S S1075 S1122 S1573 S1574 S3002**

(56) Documents Cited

**GB 1051514 A GB 1040506 A GB 0937057 A
EP 0095874 A1 WO 98/39382 A1 WO 97/09379 A1
US 3997489 A**

(58) Field of Search

**UK CL (Edition Q) C3K KLA
ONLINE: epodoc**

(54) Abstract Title
PVA-containing compositions

(57) An extrudable PVA-containing composition includes a lubricant, such as a fatty acid amide, most preferably octadecanamide and is most preferably formed into pellets by cold pressing. A plasticizer and a filler may be included in the composition, and also an additional lubricant such as a stearate.
Other compositions comprise PVA and a filler e.g. calcium carbonate and/or a superabsorbent material and/or a plasticizer.

GB 2 340 835 A

PVA-CONTAINING COMPOSITIONS

The present invention relates to PVA-containing compositions, particularly filled compositions, to methods of making such compositions and to methods of extruding PVA-containing compositions.

There is currently a significant and increasing demand for bio-degradable polymers, to replace non bio-degradable polymers which take up an ever greater amount of disposal space, such as land-fill, or need to be incinerated.

Polyvinylalcohol (PVA) is one bio-degradable polymer which is in widespread use. As a film, PVA shows a high degree of impermeability to a number of gases. Incorporated into adhesive, PVA shows high adhesive strength. PVA has significant potential in a wide range of products. However, the applications of PVA have been limited because there is currently no formulation of PVA or PVA-containing composition which can readily be extruded.

While attempts have been made to extrude articles from PVA, it has been found that melt extruded PVA becomes very unstable and significant residues become adhered to the surfaces of the extrusion apparatus, requiring very careful control of process conditions, specialised extrusion apparatus and frequent shut down of the extrusion process and purging of the apparatus.

It is known to polymerize ethylene with vinylalcohol to provide a copolymer of ethylene-vinylalcohol, in an attempt to retain the desirable properties of PVA whilst simultaneously obtaining an extrudable polymer. One such copolymer is marketed under the trade mark SOARNOL (registered trade mark of the Nippon Synthetic Chemical Industry Co, Limited). However, it is found that this copolymer has effectively lost all of the advantageous properties of PVA and is not an effective alternative to an extrudable PVA.

A chemically modified PVA is also known and sold as VINEX (registered trade mark of Air Products). This suffers, however, from the fact that some of the advantageous PVA

properties are adversely affected by the chemical modification.

The search for bio-degradable polymers is acute in relation to certain sanitary products such as diapers and sanitary towels. However, these products typically comprise superabsorbent materials and at present such materials are only available in combination with conventional non bio-degradable polymers.

The present invention is concerned, at least in preferred embodiments, with providing PVA-containing compositions, methods of manufacturing the same and methods of extruding PVA-containing compositions which overcome or at least ameliorate some of the disadvantages identified in the art.

Accordingly, a first aspect of the invention provides a PVA-containing composition comprising a blend of PVA and an amount of lubricant effective to render the blend extrudable.

The lubricant preferably comprises a fatty acid amide and the composition may advantageously further comprise a plasticiser, the resultant blend being suitable for extrusion in conventional melt-extrusion apparatus. In embodiments of the invention, a PVA-containing composition comprises up to 20%, especially 5 to 15%, plasticizer and up to 5%, especially 0.5 to 2.5%, lubricant, by weight.

The composition of the present invention is thus an extrudable PVA-containing polymer, typically with a flexural modulus similar to other extrudable polymers. Known advantageous properties of PVA, such as its high tensile strength, good puncture resistance, and good barrier characteristics are retained in an extrudable composition which can be processed on current extrusion lines, blow-moulders and injection moulders without modification, and without the processing problems such as thermal degradation and high temperature cross linking, observed in attempts to extrude articles using hitherto known PVA-containing compositions.

In embodiments of the invention, extrudable PVA-containing compositions have been

obtained comprising fully hydrolysed PVA as well as partially hydrolysed PVA, and including PVA that is 70% or more hydrolysed.

Further embodiments of the invention provide PVA-containing compositions in which the molecular weight of the PVA varies from around 20,000, in some cases from around 10,000, to greater than 150,000. Generally, the application of the present invention is not limited to PVA of any particular percent hydrolysis nor of any particular molecular weight.

A second aspect of the invention provides a filled PVA-containing composition comprising a blend of PVA plus filler. In this composition, the filler is effectively a bulking agent and is relatively inexpensive compared to the PVA, thus a composition is obtained retaining advantageous properties of PVA whilst being cheaper per unit weight to produce.

In both aspects, the invention preferably provides a PVA-containing composition in the form of pellets or tablets. These preferably have a size of between about 1mm and 5mm in diameter and are suitably obtained by a method of the invention in which PVA, preferably substantially uncompounded and in powder or granular form, is mixed with at least one of lubricant and filler, and optionally other compounding ingredients, and cold pressed to form a tablet or pellet. This cold-pressing method is substantially as described in WO-A-98/26911 in relation to different polymers.

With this method, the ingredients can be uniformly mixed and compounded in the correct proportions for the final product, and made into a form that is easier to handle than powder. In addition, since the mixture is cold pressed rather than melted, problems of thermal degradation or variation in properties are reduced.

References to "cold pressing" are intended to imply applying pressure to the powder to cause agglomeration without substantial melting of the polymer. The temperature is preferably less than about 100 degrees celsius, more preferably less than about 70-80 degrees celsius. Preferably heat is not applied directly to the mixture. However, heat may be generated by mixing and/or pressing, and this may be allowed to warm the mixture, or cooling may be provided. It is permissible for some heat to be applied directly if necessary to facilitate

binding. Some melting of the polymer or other ingredients may occur, particularly on a microscopic scale as a result of pressure at the interface between adjacent particles, but it is important that the bulk of the polymer granules do not liquify.

Preferably, the mixture is compressed in discrete quantities into tablets or pellets, for example in a tablet press; this may provide more reliable agglomeration.

However, it is possible for the mixture to be extruded under pressure through an orifice, the pellets forming following exit of the mixture from the orifice. In such a case, binder or moisture may be added to the mixture, preferably as the mixture is extruded, or after preliminary mixing of the constituents.

Preferably, the mixture is substantially dry, but includes sufficient residual moisture to bind the tablets or pellets on pressing. This avoids the need to add a separate binder, and allows the tablets or pellets to be broken more easily as they enter the extruder simply by drying them further. When water is relied upon for binding, it is desirable to ensure that the tablets or pellets are dried prior to extruding, for example at between 40 and 80 degrees celsius for 4-8 hours; this alleviates problems of vapour formation during extrusion. The moisture content is desirable to form the tablets, but after forming, the tablets should in most cases retain their shape even when dried.

Preferably, the moisture content is less than about 10% by weight, and preferably greater than 0.01% by weight, more preferably less than about 5%. If the pellets or tablets are extruded or otherwise formed at relatively low pressures, however, the moisture content may be about 20% or even higher to ensure binding. If the pellets are too moist, they may tend to stick together, inhibiting flow, and drying after forming may be desirable.

The moisture may comprise residual moisture in the polymer or in one or more of the compounding ingredients. In this way, moisture can be provided automatically simply by not drying the ingredients fully prior to mixing.

It is preferred that the filled PVA-containing composition is extrudable, and hence preferred

that the filled PVA-containing composition further comprises an effective amount of a lubricant to render the composition extrudable. The lubricant suitably comprises a fatty acid amide or a plasticiser or a mixture of both a fatty acid amide and a plasticiser.

The lubricant in compositions of the invention is provided so as to improve the thermal stability of the composition under extrusion. The lubricant may be referred to as an internal lubricant, in that its function is to improve lubrication between the polymer chains. Compositions of the invention may be intended for use in or in connection with food stuffs, and hence it is preferred that the lubricant is approved for food use. It is further preferred that the lubricant is a fatty acid amide, and particularly a straight or branched C_{12} - C_{24} fatty acid amide, more particularly C_{16} - C_{20} . Particularly and surprisingly good results are obtained if the lubricant comprises stearamide, a straight chain C_{18} fatty acid amide.

The compositions of the invention typically further include a plasticiser, to lower the melt temperature of the polymer under extrusion. The plasticiser may suitably be selected from glycerine, ethylene glycol, triethylene glycol, low molecular weight polyethylene glycols and low molecular weight amides. A particularly preferred plasticiser comprises or consists of glycerol.

While the proportion of components present may vary in compositions of the invention, embodiments of the invention generally comprise, by weight, up to 50% filler and up to 5% lubricant. More particular embodiments of the invention comprise, by weight, 5-50% filler, 40-80% PVA, up to 5% lubricant and 5-20% plasticizer.

Compositions of the invention are thus extrudable, but it may be that ease of extrusion depends partly upon the state of the extrusion apparatus, in particular the roughness of surfaces in the apparatus. In further embodiments of the invention, the compositions comprises an additional lubricant, which may be referred to as an external lubricant, to prevent or reduce adhesion of the composition to such surfaces. This external lubricant is typically present at 0.001 to 0.1% by weight of the composition and preferably approved for food use, in the same way as the internal lubricant. Stearate salts are suitable external lubricants, in particular magnesium, lead or zinc stearates.

Fillers for incorporation into compositions of the invention may suitably be selected from conventional polymer fillers. Typically the filler is an inert, inorganic material and a particularly preferred filler is or comprises talc, calcium carbonate. In a specific embodiment of the invention, this talc may be micronised, such as in particles with a mean size of about 20 microns and may further be coated, such as with a stearate. One such coated, micronised talc is available from Croxton and Gary as 90T (trade mark of Croxton and Gary).

It is further an option for the filler to comprise or consist of a superabsorbent material. In a specific embodiment of the invention, described in an example below, a filled PVA-containing composition comprises a superabsorbent which contains cross-linked sodium polyacrylate (available from Alloid Colloids as SALISORB CL31 (registered trade mark)). Filled compositions of the invention may nevertheless contain superabsorbent material of substantially any type. Incorporation of such superabsorbent material confers the particular advantage that sanitary products such as diapers and sanitary towels, hitherto major components of waste storage sites such as land-fill sites, may now be made of or comprise a significant proportion of bio-degradable material.

A number of water-absorbent compositions are known and suitable for use as the filler in embodiments of the invention. For example, U.S. Patent numbers 3,954,721 and 3,983,095 disclose preparations for derivatives of copolymers of maleic anhydride with at least one vinyl monomer in fibrous form. The fibrous copolymers are rendered hydrophillic and water-swellaable by reaction with ammonia or an alkali metal hydroxide. U.S. Patent No. 3,810,468 discloses lightly cross-linked olefin-maleic anhydride copolymers prepared as substantially linear copolymers and then reacted with a diol or a diamine to introduce cross-linking. The resultant lightly cross-linked copolymers are treated with ammonia or an aqueous or alcohol solution of an alkali metal hydroxide. U.S. Patent No. 3,980,663 describes water-swellaable absorbent articles made from carboxylic polyelectrolytes via cross-linking with glycerine diglycidyl ether. These patents are incorporated herein by reference.

European Published Application No. 0 268 498 (incorporated herein by reference) describes a water-absorbent composition formed by causing a substantially linear polymer of water-

soluble ethylenically unsaturated monomer blends comprising carboxylic and hydroxylic monomers to cross-link internally.

Further examples of water-absorbent compositions are those produced from a copolymer of an α,β unsaturated monomer having at least one pendant unit selected from a carboxylic acid group and derivatives thereof and a copolymerisable monomer. A proportion of the pendant units are present in the final copolymer as the free acid and a proportion as the salt of the acid. These copolymers are capable of being cross-linked, either internally or with a variety of cross-linking agents, to form the water-swellaable composition. Examples of water-swellaable compositions of this type can be found in U.S. Patent Nos 4,616,063, 4,705,773, 4,731,067, 4,743,244, 4,788,237, 4,813,945, 4,880,868 and 4,892,533 and European Patent Nos 0 272 074 and 0 264 208 and European Published Application No. 0 436 514 which are incorporated herein by reference.

Derivatives of carboxylic acid groups include carboxylic acid salt groups, carboxylic acid amide groups, carboxylic acid imide groups, carboxylic acid anhydride groups and carboxylic acid ester groups.

Other examples of water-absorbent compositions can be found in US 4798861, WO93/17066, WO93/255735, WO 93/24684, WO93/12275, European Published Application Nos 0 401 044, 0 269 393, 0 326 382, 0 227 305, 0 101 253, 0 213 799, 0 232 121, 0 342 919, 0 233 014, 0 268 498 and 0 397 410, British Patent Application Nos 2 082 614, 2 022 505, 2 270 030, 2 269 602 and 2 126 591, U.S. Patent Nos 4,418,163, 4,418,163, 3,989,586, 4,332,917, 4,338,417, 4,420,588 and 4,155,957 and French Patent Application No. 2 525 121 which are all incorporated herein by reference.

The extrudable compositions of the invention are suitable for manufacture of substantially any article made using currently extrudable polymers, including films and bottles and any other articles. The compositions are suited to manufacture of filaments and fibre, for use in spunbond, non-woven and melt-blowing applications. The composition is suitable also for manufacture of such articles as agri-chem sachets, mulch films, plant pots, domestic bags, diapers, drinking straws, fem care products, hangers, incontinence pads, sachets, six pack

rings, disposable clothing, expanded foams, gloves, film canisters, golf tees, shot gun cartridges, bed pans, bottles, bowls, cotton buds, hospital curtains, "one-use" sterile products and packaging materials.

Particularly good results have been obtained in embodiments of the invention having the following make-up, by weight:-

- (a) 40 to 70% PVA;
- (b) 20 to 50% filler, preferably a micronised inorganic material such as talc, preferably coated with stearate;
- (c) 8 to 15% plasticizer, preferably glycerol;
- (d) 0.5 to 1.5% internal lubricant, preferably a fatty acid amide, most preferably octodecanamide; and
- (e) 0.0001 to 0.1% external lubricant, preferably stearate.

The composition may contain residual moisture, sufficient to enable the composition to be bound as a cold-pressed tablet.

Further advantageous results have been obtained in compositions of the invention comprising, by weight:-

- 50 to 60% PVA;
- 30 to 40% stearate-coated calcium carbonate;
- 8 to 15% glycerol;
- 0.5 to 1.5% octadecanamide; and
- 0.0001 to 0.1% zinc stearate.

In a third aspect, the invention provides a method of making an extrudable PVA-containing composition comprising blending PVA with a lubricant, said lubricant including a fatty acid amide. The method preferably comprises blending PVA with a fatty acid amide in the presence of an amount of moisture sufficient to bind the composition into tablets or pellets upon cold pressing.

The amount of lubricant blended with the PVA is typically restricted by the fact that, above a certain percent, excess lubricant separates out from the blend, and generally lubricant is

blended at up to 5% by weight of the PVA present. The method thus conveniently enables tablets or pellets of the composition to be prepared as the feedstock for an extrusion. Blending of the components of the composition is achieved using conventional apparatus, one such example being a high speed blender.

The method may optionally comprise adding small amounts of moisture to the components to be blended, such as by dripping water into the blend. Preferably, PVA and lubricant are fed into a high speed mixer gravimetrically.

In a fourth aspect, the invention provides a method of making a PVA-containing composition comprising blending PVA and a filler, wherein the filler comprises a superabsorbent material. It is preferred that blending is carried out in the presence of sufficient moisture to bind the composition into tablets or pellets upon cold pressing, the moisture optionally being present in the starting materials of the blend or being introduced into the blend, such as by drip-feeding.

A fifth aspect of the invention provides a method of extruding a PVA-containing composition so as to form an extruded product which contains PVA, comprising:-

blending PVA with at least one component selected from a lubricant and a filler; and

cold pressing the resultant blend into pellets or tablets;

wherein the pellets or tablets comprise the polymer feedstock for extrusion of an extruded product containing PVA.

The PVA is preferably blended with one or more lubricant or filler components in the presence of sufficient moisture to bind the blend upon cold pressing. An advantage of the method is that the PVA-containing feedstock for the extrusion step is obtainable substantially without melting of the PVA. This improves the stability of the PVA during subsequent extrusion. Hitherto, as has been recognised in the present invention, attempts to extrude a PVA-containing feedstock largely failed as the PVA already had a heat history, ie had been

wholly or partially melted in processing stages prior to the extrusion stage. The present invention avoids the disadvantage of introducing such a heat history into the PVA-containing composition.

A sixth aspect of the invention provides a method of extruding a PVA-containing composition comprising blending PVA and at least one optional component selected from a lubricant and a filler to form a feedstock for an extrusion process, the feedstock being in the form suitably of powder, pellets or tablets, and extruding the feedstock into a product, wherein the feedstock is prepared substantially without melting of the PVA.

A seventh aspect of the invention provides a method of extruding a polymer composition containing a heat sensitive polymer, comprising blending the heat sensitive polymer with one or more optional components selected from a filler and a lubricant to form a feedstock for an extrusion process, the feedstock being suitably in the form of powder or pellets or tablets, and extruding the feedstock into an extruded product, wherein the feedstock is prepared substantially without melting of the heat sensitive polymer.

Optional and preferred features of the first and second aspects of the invention are, similarly, optional and preferred features of the third to seventh aspects of the invention.

The invention is now described in the following non-limiting examples.

Example 1

A blend of, by weight, approximately 60% fully hydrolysed PVA, 30% calcium carbonate, 10% glycerol, 0.01% zinc stearate and 1% octadecanamide was prepared in a high speed blender. It was found to have a white/cream colour with the following properties:-

density	1.65 g/cm ³
melt density	1.46 g/cm ³ at 200°C (under ISO 1183)
MFR	357 (10 mins/200°C/21.6 kilograms, under ISO 1133)
melt temperature	200°C

processing temperature	190 - 200°C
residence time	up to 15 minutes
drying time	4 hours at 80°C

Example 2

A blend was prepared in a similar way to example 1 of, by weight, approximately 60% partially hydrolysed PVA, 30% calcium carbonate, 10% glycerol, 0.01% zinc stearate and 1% octadecanamide. This was found to have the following properties:-

density	1.65 g/cm ³
melt density	1.38-1.40 g/cm ³ at 190°C (under ISO 1183)
MFR	22 (10 mins/190°C/5 kilograms, under ISO 1133)
apparent melt viscosity	236/49 (Pa.s 1,000s/10,000s)
melt temperature	200°C
processing temperature	190-200°C
residence time	up to 15 minutes
drying time	4 hours at 80°C

Example 3

The PVA-containing compositions of examples 1 and 2 were examined for their extrudability in injection-moulding machines made by Brabender, Killion, Windsor, Hesas, Battenfield, Fischer, Demag and Arburg. Extrusion processing was carried out using a single full flight screw with constant pitch. The barrel temperature had a profile of 180-200°C (melt 190-210°C) and the screw speed varied typically between 20 and 120 rpm. Shut down of the apparatus was carried out by maintaining the temperature for up to 15 minutes with screw rotation stopped, over a period of 3 hours reducing the temperature to 100°C with screw rotation stopped and subsequently completing the shut down by turning the machine off.

The compositions of both examples 1 and 2 were satisfactorily extruded into a range of films and tubes blow-moulded containers of various sizes and colours and injected moulded

products.

Examples 4-9

PVA-containing compositions were prepared as blends of the following components in the amounts shown:-

<u>EXAMPLE</u>						
	4	5	6	7	8	9
<u>Components</u>						
PVA - fully hydrolysed	-	-	-	50	60	55
PVA - partially hydrolysed	50	60	55	-	-	-
Calcium carbonate (coated)	40	30	30	40	30	30
Glycerol	9	9	14	9	9	14
Octadecanamide	1	1	1	1	1	1
Zinc Stearate	0.01	0.01	0.01	0.01	0.01	0.01

Example 10

A further filled PVA-containing compositions was prepared as a blend of, by weight, approximately 60% partially hydrolysed PVA, 30% cross-linked sodium polyacrylate (a superabsorbent), 9% glycerol, 1% octadecanamide and 0.01% zinc stearate.

As far as extrusion apparatus is concerned, it is advantageous to use chrome plated screws and for the melt flow path to use chrome plated surfaces and gradual tapers to streamline the melt.

The invention thus provides PVA-containing compositions for use in the manufacture of biodegradable articles. The invention extends to combinations of all features individually disclosed. In particular, optional or preferred features of any of the apparatus, product or method aspects may be combined with features of other aspects.

CLAIMS

1. A PVA-containing composition, comprising a blend of PVA and an amount of lubricant effective to render the blend extrudable.
2. A composition according to Claim 1 wherein the lubricant comprises a fatty acid amide.
3. A composition according to Claim 2 wherein the fatty acid amide is a straight or branched C_{12} - C_{24} fatty acid amide.
4. A composition according to Claim 2 or 3 wherein the composition further comprises a plasticiser.
5. A composition according to Claim 4 wherein the plasticiser is selected from ethylene glycol, glycerine, glycerol, triethylene glycol, low molecular weight polyethylene glycols and C_2 - C_8 amides.
6. A composition according to any of Claims 1 to 5 comprising up to 5% lubricant, by weight.
7. A composition according to any of Claims 1 to 6 comprising up to 20% plasticiser, by weight.
8. A composition according to any of Claims 1 to 7, in the form of a tablet or pellet obtainable by cold-pressing
9. A filled PVA-containing composition, comprising a blend of PVA plus filler.
10. A composition according to Claim 9 wherein the filler comprises inert, inorganic material.

11. A composition according to Claim 9 wherein the filler comprises a superabsorbent material.
12. A composition according to Claim 9 wherein the filler comprises both an inert, inorganic material and superabsorbent material.
13. A composition according to Claim 9, 10 or 12 wherein the inorganic filler comprises calcium carbonate.
14. A composition according to any of Claims 9-13 further comprising a lubricant.
15. A composition according to Claim 14 wherein the lubricant comprises a fatty acid amide.
16. A composition according to any of Claims 14 to 15 comprising, by weight, up to 50% filler, up to 5% lubricant and up to 20% of a plasticizer.
17. A composition according to any of Claims 14 to 16 comprising, by weight, 5-50% filler, 0.5 to 2.5% lubricant, 5 to 15% plasticizer and 40-80% PVA.
18. A composition according to any of Claim 1-17, further comprising an additional lubricant component to reduce adhesion of the composition to surfaces.
19. A composition according to Claim 18 wherein the lubricant comprises a stearate.
20. A composition according to any of Claims 9 to 19 in the form of a tablet or pellet obtainable by cold-pressing.
21. A PVA-containing composition comprising, by weight:-
 - 40 to 70% PVA;
 - 20 to 50% filler;
 - 8 to 15% plasticizer;

0.5 to 1.5% internal lubricant; and

0.0001 to 0.1% external lubricant.

22. A composition according to Claim 21 comprising, by weight:-

50 to 60% PVA;

30 to 40% stearate-coated calcium carbonate;

8 to 15% glycerol;

0.5 to 1.5% octadecanamide; and

0.0001 to 0.1% zinc stearate.

23. A method of making a PVA-containing composition comprising blending PVA with a lubricant, said lubricant including a fatty acid amide.

24. A method according to Claim 23 comprising blending PVA with a fatty acid amide in the presence of an amount of moisture sufficient to bind the composition into tablets or pellets upon cold pressing.

25. A method according to Claim 23 and 24 comprising blending, in a high speed blender, PVA with up to 5% by weight of lubricant.

26. A method according to any of Claims 23 to 25 comprising adding moisture to the components to be blended, such as by dripping water into the blend.

27. A method according to any of Claims 23 to 26 wherein PVA and lubricant are fed into a high speed mixer gravimetrically.

28. A method of making a PVA-containing composition comprising blending PVA and a filler, wherein the filler comprises a superabsorbent material.

29. A method according to Claim 28 comprising blending PVA and a superabsorbent material in the presence of sufficient moisture to bind the composition into tablets or pellets upon cold pressing.

30. A method of extruding a PVA-containing composition so as to form an extruded product which contains PVA, comprising:-

blending PVA with at least one optional component selected from a lubricant and a filler;

cold pressing the resultant blend into pellets or tablets;

wherein the pellets or tablets comprise the polymer feedstock for extrusion of an extruded product containing PVA.

31. A method according to Claim 30 comprising blending PVA with one or more optional components in the presence of sufficient moisture to bind the blend upon cold pressing.

32. A method of extruding a PVA-containing composition comprising blending PVA and at least one optional component selected from a lubricant and a filler to form a feedstock for an extrusion process, the feedstock being in the form suitably of powder, pellets or tablets, and extruding the feedstock into a product, wherein the feedstock is prepared substantially without melting of the PVA.

33. A method of extruding a polymer composition containing a heat sensitive polymer, comprising blending the heat sensitive polymer with one or more optional components selected from a filler and a lubricant to form a feedstock for an extrusion process, the feedstock being suitably in the form of powder or pellets or tablets, and extruding the feedstock into an extruded product, wherein the feedstock is prepared substantially without melting of the heat sensitive polymer.



Application No: GB 9818604.2 **Examiner:** Miss M M Kelman
Claims searched: 1 to 8, 18 to 20 (when appendant to claims 1 to 8),
 21 to 27 and 30 to 32 (when a lubricant is included in the composition extruded) **Date of search:** 17 November 1999

Patents Act 1977
Search Report under Section 17

Databases searched:

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:

UK CI (Ed.Q): C3K KLA

Int CI (Ed.6):

Other: ONLINE: EPODOC

Documents considered to be relevant:

Category	Identity of document and relevant passage	Relevant to claims
X	GB 1051514 A DENKI KAGAKU see whole document	1,2,3,6,23,32
X	GB 1040506 A MONSANTO see claims 1 to 3, 11, 17 and 23, page 3, lines 68 to 88 and line 125 to page 4, line 9, page 7, lines 106 to 113, and Examples 4, 6, 7 and 9	1,4,5,6,7
X	GB 0937057 A REVERTEX see the claims and page 2, lines 19 to 28	1,4,7,8
X	EP 0095874 A1 MILLER see the claims and Examples 1 to 8 and 16	1,2,3,4,6,7,23,25,32
X,P	WO 98/39382 A1 SOLPLAX see claims 1,4,9,13,17,18 and 19, page 10, lines 11 to 19, and Examples 4,5 to 9F, 11A to 11C, 12,18A and 18B	1,2,3,4,5,6,7,8,23,25
X	WO 97/09379 A1 SOLPLAX see the claims and Examples 1 to 3 and 30 to 37	1,2,3,4,5,6,7,23,27

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.



Application No: GB 9818604.2 **Examiner:** Miss M M Kelman
Claims searched: 1 to 8, 18 to 20 (when Date of search: 17 November 1999
appendant to claims 1 to 8),
21 to 27 and 30 to 32 (when
a lubricant is included in the
composition extruded)

Category	Identity of document and relevant passage	Relevant to claims
X	US 3997489 A COKER see the claims and Examples 28,29,35,36 and 72	1,2,3,4,5,6,7,23,32

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.